

12

EUROPEAN PATENT APPLICATION

21 Application number: 89115953.5

51 Int. Cl.⁵: **C09D 5/38 , H05B 6/64**

22 Date of filing: 30.08.89

30 Priority: 01.09.88 US 239544

43 Date of publication of application:
07.03.90 Bulletin 90/10

64 Designated Contracting States:
AT BE CH DE ES FR GB GR IT LI LU NL SE

71 Applicant: **JAMES RIVER CORPORATION OF VIRGINIA**
Tredegar Street P.O. Box 2218
Richmond, VA 23217(US)

72 Inventor: **Pollart, Kenneth A.**
524 Surrey Lane
Neenah Wisconsin 54956(US)
Inventor: **Lafferty, Terrence P.**
901 Hewitt St.
Neenah Wisconsin 54956(US)

74 Representative: **Schupfner, Gerhard D. et al**
Müller, Schupfner & Gauger Karlstrasse 5
Postfach 14 27
D-2110 Buchholz/Nordheide(DE)

54 **Microwave interactive coating compositions and heating elements.**

57 A microwave interactive coating composition and microwave reactive paper and paperboard heaters comprising the coating composition are disclosed. The coating compositions which comprise finely divided carbon, a finely divided microwave reactive metallic component, a powdered inert solid and a binder are capable of producing microwave reactive heaters comparable to those produced by vapor deposition of metals on a carrier film.

EP 0 357 008 A2

MICROWAVE INTERACTIVE COATING COMPOSITIONS AND HEATING ELEMENTS

This invention relates to improvements in microwave interactive coating compositions and to microwave interactive heating elements comprising a microwave transparent substrate coated with such compositions.

The cooking of food and heating of other microwave interactive substances by microwave radiation has become increasingly popular and important in recent years because of its speed, economy, and low power consumption. One of the major drawbacks of microwave ovens for preparation of foods has been their inability to brown or sear the food product to make it similar in taste and appearance to conventionally cooked food. Crisping of certain foods, e.g., the crusts of pies or pizzas, or the surface of fish fillets, potato cakes, or the like, may be accomplished only by means of special packages or utensils.

Several methods have been attempted in the prior art to overcome the browning and crisping problems. One such method for browning or crisping foods or for concentrating heat to produce superheated temperatures in selected areas of packages involves the use of a metallized coating on paperboard. In some instances, metal particles are vacuum deposited onto a film, preferably a polyester film and the metallized film then laminated onto paper or paperboard. The thus metallized paper or paperboard can then be used in a microwave oven to heat, brown or sear food items placed on the metallized paperboard or in packages comprising metallized paperboard. While such structures can be very effective as heaters, the vacuum deposition process does not readily lend itself to coating selected areas of the film or the application of varying amounts of metal particles or metallized coating to selected areas of the finished carton or structure.

Other methods of forming microwave responsive heating elements involve dispersing particles which are lossy microwave energy absorbers, e.g. carbon, metals, and metal alloys, in a binder and forming a sheet or laminate comprising the dispersed particles. Turpin, U.S. Patent No. 4,190,757 discloses heaters which comprise a layer of particulate lossy materials, e.g. carbon, iron and various metal oxides, or alloys, in an inorganic binder, e.g. sodium silicate. U.S. Patent No. 4,264,668 to Balla discloses a heating element made up of a layer of carbon black in an acrylate binder laminated between a carrier layer, e.g. paper, cardboard or plastic material, and an outer layer of thermoplastic material. European Patent Application Publication No. 242,952 discloses a heating element made up of a metal or metal alloy in flake form in a thermoplastic dielectric matrix on a dielectric substrate.

SUMMARY OF THE INVENTION

The present invention provides an improved microwave interactive composition which may be coated or printed onto a substrate and which overcome problems inherent in prior art coatings. The composition can be printed in various coating patterns and coating thicknesses using conventional printing or coating processes. The compositions also make possible relatively precise control of heating temperatures and are useful in a wide variety of applications.

A preferred embodiment of the present invention includes microwave interactive coating compositions containing a microwave reactive material comprising carbon, at least one finely divided metal or metal oxide, a powdered solid temperature moderator, and a binder in a suitable carrier liquid. Other embodiments of the invention include a microwave interactive structure comprising a substrate suitably paper, coated with a composition consisting essentially of finely divided carbon, at least one flaked or powdered metal component, a solid temperature moderator, and a dielectric organic solid binder.

Other, less preferred, embodiments of this invention include compositions consisting essentially of microwave reactive metal particles, finely divided carbon, and a binder. Another of the less preferred embodiments of this invention comprises compositions consisting essentially of carbon black, a powdered solid temperature moderator, and a binder.

In a preferred embodiment of the invention, the microwave interactive composition is coated directly onto paper or paperboard. Alternatively, the coating composition may be applied to a film which is then laminated to paper or paperboard. In accordance with a preferred embodiment, a microwave heating element is produced by printing or coating paper or paperboard, or a heat stable polymeric film, with a fluid composition comprising high surface area finely divided carbon, at least one finely divided metal or metal compound, a finely divided inert solid temperature moderator, and a binder.

DESCRIPTION OF THE DRAWING

Fig. 1 of the drawing illustrates graphically the heating response obtained with heating elements produced from a preferred embodiment of the microwave interactive composition of this invention.

Fig. 2 of the drawing illustrates graphically the performance of heating elements produced from our preferred compositions by printing the coating onto paper with a rotogravure printing process as compared with a heater produced by conventional vapor deposition of aluminum on polyester film and laminated to paper or paperboard.

DETAILED DESCRIPTION OF THE INVENTION

Microwave reactive materials (MRM) are capable of converting microwave energy to heat. The microwave reactive materials included within the scope of this invention are carbon in the form of carbon black or graphite, and a finely divided metal component, e.g. aluminum, tin, bronze, nickel, and the like, which are conductive or semiconductive or ferromagnetic materials capable of converting microwave radiation energy to heat. The inert powdered solid temperature moderators suitable for use in these formulations include clays (e.g. kaolin and English china clays, alumina, alumina hydrate (aluminum hydroxide), aluminosilicates, silica, calcium carbonate, titanium dioxide, and the like. The temperature moderator should be essentially inert and substantially unresponsive or only mildly responsive to microwave radiation. Preferred binders comprise synthetic resins in a suitable vehicle; especially preferred binders include polymer latex formulations marketed for this purpose.

The relative proportions by weight of carbon to metal in the composition may be within the range of from about 1:2 to about 2:1 with a preferred range of from about 1:1.5 to 1.5:1. The preferred ratio of carbon black to aluminum flake is about 0.6. The content of the inert temperature moderator ingredient, e.g. clay, in the composition may range from about 10 percent by weight of the total (dry basis) weight to about 35 percent. As the content of the temperature moderator is increased it is possible to produce heaters with increasingly higher temperature responses with a heat absorbent load without experiencing ignition of the paper or paperboard substrate when placed in a microwave oven without a load. A load is defined herein as the food, water, or other material normally present during microwave exposure. The relative proportions of binder solids to the remaining solids making up the coating may be in the range of from about 0.3:1 to 1:1. However, as the binder level is increased, the temperature response of the microwave interactive coating is reduced significantly, both with and without a load. It is preferred to use only enough binder to adequately bond the coating pigments (the other solids) to the substrate. With paper or polyester film as the substrate, a binder solids content in the range of from about 30 to about 40 weight percent of the total coating is preferred. While latex formulations are preferred as binders, a non-aqueous solvent formulation with a binder, such as the product marketed by Morton Chemical Company under the trade name Morez 100, also has been found suitable for use.

As illustrated in the specific examples in this patent application, the type and amount of microwave reactive materials contained in the coating composition largely determines the degree of interaction with the microwaves and hence the amount of heating generated. In a preferred embodiment of this invention, the amount of heat generated is a function of the relative proportion of the coating components and the thickness of the coating on the substrate.

In a preferred embodiment of this invention the microwave reactive material is carbon combined with a metal component. Various metals, metal alloys, and metal compounds in fine particle form are known microwave reactive materials. Microwave reactive metals preferred in this invention include aluminum, iron, nickel, copper, tin, and silver. The metal component may be in powder form, flake form or any other finely divided form suitable for use in coating and printing processes.

In the preferred embodiment of this invention, the microwave reactive material is one which is suitable for use in food packaging and is normally separated from contact with the food by paper or paperboard or by a thermally stable film, e.g. a biaxially oriented polyethylene terephthalate.

It is preferred that the reactive composition demonstrate rapid heating to a desired temperature, with subsequent leveling off of the temperature, and without igniting or destroying the substrate upon exposure to microwave radiation in the absence of a load. The temperature at which the microwave reaction material levels off is hereinafter referred to as the operating temperature. Generally, the microwave reactive material will operate at a temperature ranging from about 275° to about 480° F.

The microwave reactive components and inert material are combined with a binder to form a coating

composition. The binder used in this invention may comprise an aqueous or non-aqueous solution or dispersion of a polymer precursor that can be used as a vehicle for the powdered solid components, particularly those which are suitable for use in a printing ink or printing process. The binder must have good thermal resistance and suffer little or no chemical degradation at the temperatures generated by the microwave heating process. The binder must also have an adhesive ability which will allow it to bind the particles together and adhere the composition to the substrate, preferably paper or paperboard or an oriented film.

Preferred binders for the present invention may be selected from water based emulsion polymers, including acrylic latex emulsions, and non aqueous solvent systems as above mentioned.

The binder and the powdered solid microwave reactive components are combined in suitable relative proportions such that the microwave reactive solids, in the form of a relatively thin coating on the substrate will raise the temperature of a load, e.g. a food item, to the desired level in a reasonable amount of time. The amount of dielectric components must also be sufficient to prevent arcing of the microwave reactive components in the heating element. The heating element may comprise a part or parts of a food package or container, or may consist of a separate heater which may be included in or used in conjunction with a food container or package. The heater may comprise a component of other structures unrelated to food processing where rapid controlled heating by microwave energy is desirable.

Preferably only enough binder is used to adequately bond the solid coating components to one another and to the substrate. As the ratio of the binder to microwave reactive material, on a solids basis, is increased, the temperature of the microwave reactive coating is significantly reduced, both with and without a load. In a preferred embodiment, where the microwave reactive material is a mixture of carbon black and aluminum flake with clay as a moderator and the binder is an acrylic emulsion, the pigment to binder ratio, on a weight basis, should be about 2:1 or higher. The ratio of carbon black to aluminum flake can be varied from about 2:1 to 1:2 without having a major effect on temperature response.

Other materials can be included in the coating composition, such as surfactants, dispersion aids and other conventional additives used in coating and printing compositions to facilitate application of the coating composition to the substrate by rotogravure or other suitable printing or coating methods. The coating can be applied using conventional printing and coating processes, e.g., rotogravure, silk screen, flexography, air knife, roll, blade, etc. After the coating composition has been applied it can be dried using conventional drying ovens normally provided in web printing and coating processes.

Theoretically, any amount of coating can be used in the present invention. In a preferred embodiment, when the coating material is a mixture of aluminum flake and carbon black admixed with clay and binder solids, the amount of coating will range from about 2 to about 20 pounds per 3000 sq. ft. ream depending on the composition and the desired temperature required for a particular application. The coating composition can generally be coated upon any substrate, especially flexible materials, eg. paper, paperboard, nonwovens, or any suitable film material. Substrates including various uncoated, clay coated, grease proof and parchment papers and polyester films have been successfully used as substrates in our process.

A desirable feature for the microwave reactive coatings is that the coating should have a heating response which results in rapid heating of the load in response to microwave radiation so that the temperature of the coating rises rapidly and then remains at a constant level. It is desirable also, for the temperature of the coating to be self limiting in the absence of a load to avoid ignition of the substrate. These desirable features are accomplished by the composition of our invention as will be apparent from the accompanying specific examples.

The advantages of the process of this invention result from the ability of the compositions to provide microwave interactive coatings on paper or paperboard by conventional coating or printing processes. The coatings can be applied in various patterns and in varying amounts using conventional printing and coating techniques at precise locations on the substrate. Such precise control of amounts of a microwave interactive coating composition applied to a predetermined part of a substrate is not possible with present vacuum metallization coating methods. Coatings of different thickness can be applied simultaneously. Such non-uniform coatings are useful for heating foods which require different levels of temperature and which are contained in the same paper or paperboard container. Printing processes require fewer steps, are more continuous processes and avoid the need for multiple steps involved in the metallization of film and lamination of the metallized film to a substrate.

The following examples of test results demonstrate particular embodiments of this invention and some of the possible variations in compositions and coatings which may be adapted to varying consumer product needs.

In the following examples, all coating formulations were applied to a 40 lb/3000 sq. ft. uncoated, bleached kraft paper with a Bird applicator and dried on a photo drier at 200° F. Unless otherwise specified,

the binder used was a combination of Rhoplex B-15, an acrylate latex supplied by Rohm & Haas Company and Lucidene 602, a styrene/acrylic latex supplied by Morton Chemical Company and commonly used in aqueous printing inks.

In all cases the carbon black was dispersed (using a shot mill) into part or all of the Lucidene 602 binder being used in the formulation with additional water added as necessary to obtain the desired viscosity. After the carbon black was uniformly dispersed, it was transferred to a container equipped with a propeller type mixer. The remaining binder (Lucidene 602 and/or Rhoplex B-15) as well as the remaining components were gradually added along with additional water as needed. In each case, agitation was continued until a uniform mixture was obtained. The heater response of these coatings was determined by placing a 4 inch by 5.5 inch sample of the coated paper with its short edges taped to a 6 inch by 6 inch sample of 150 lb/3000 sq. ft. paperboard in a Litton microwave oven (Model 2238, 700 watt rating). The sample was supported 2 inches off the bottom of the oven with a glass ring and the temperature response was measured with a Hughes Probeye Thermal Video System.

EXAMPLE 1

A coating composition was prepared as described above with 65 weight percent Huber Arosperse 47 carbon black, 12 weight percent Lucidene 602 and 23 weight percent Rhoplex B-15 (based on the weight of the binder solids). Paper coated with this composition was tested under the conditions described above with the results shown in Table I.

TABLE I

	Coat Wt. lb/rm		Heater Response in Degrees F.				
	Total	Active ¹	20sec	40sec	60sec	90sec	130sec
No Load	2.0	1.3	387	ign ²	--	--	--
With Load	2.0	1.3	225	279	279	306	306

¹Active ingredient, i.e. carbon black

²Paper substrate ignited

These tests demonstrate that it is very difficult to control the heating response with a carbon coating. Coat weights with as little as 2 lb/3000 sq. ft. will cause the paper to ignite in less than 40 seconds when exposed to microwaves with no load present. With a 200 g water load in the oven, the coating surface heated to only 279°-306°F. We have observed that almost any coating of this type (carbon black or graphite + binder) capable of producing an acceptable heating response with a 200 g water load will ignite a paper or paperboard substrate under no load conditions.

EXAMPLE 2

Coating compositions were made up of 64 weight percent (based on the dry weight of the solids) of aluminum flake marketed under the trade name Hydrolac W60 by Obron Corporation in a binder of 1 part Lucidene 602 and 2 parts Rhoplex B-15 by weight. Paper test sheets coated with varying amounts of the composition were tested as in Example 1 with the results shown in Table II.

TABLE II

	Coat Wt. lb/rm		Heater Response in Degrees F.				
	Total	Active ¹	20sec	40sec	60sec	90sec	130sec
No Load	5.7	3.6	280	280	280	280	306
	17.5	11.2	ign ²	--	--	--	--
With Load	5.7	3.6	120	140	140	140	160
	17.5	11.2	333	387	414	441	468

¹Active ingredient, i.e. aluminum flake²Paper substrate ignited

It will be observed that coatings produced from aluminum flake in a binder are relatively ineffective heaters. At the lower coat weights, such as 5.7 lb/3000 sq. ft., the samples do not ignite when placed in a microwave oven with no load but with a 200 g water load the heater response is only 140°-160° F. When the coat weight is increased enough to provide a good heater response with a load, for example 7.5 lb/3000 sq. ft., the coated paper sheet will ignite when placed in the microwave oven with no load.

EXAMPLE 3

A composition was prepared in accordance with this invention from carbon black, finely divided aluminum flake and kaolin clay dispersed in a mixture of one part by weight Lucidene 602 and two parts Rhoplex B15 by weight based on their resin solids content, which supply the binder material. The compositions contained 19 weight percent carbon black marketed under the trade name Arosperse 47 by the Huber Corporation; 35 weight percent aluminum flake marketed by Obron Corporation under the trade name Hydrolac W60; 18 weight percent Georgia Kaolin, Premier No. 1 grade; and 33 weight percent (basis resin solids of a 1:2 mixture of Lucidene 602 and Rhoplex B15.

Test sheets of coated paper with coating weights in the range of 3.9 to 10 pounds per 3000 square feet were tested as in Examples 1 and 2 with the results shown in Table III, and in Fig. 1 of the drawing.

TABLE III

	Coat Wt. lb/rm		Heater Response in Degrees F.				
	Total	Active ¹	20sec	40sec	60sec	90sec	130sec
No Load	3.9	1.9	320	340	347	362	362
	5.0	2.5	387	387	412	437	437
	6.7	3.3	468	468	441	441	441
	10.0	4.9	484	ign ²	--	--	--
With Load	3.9	1.9	140	180	200	220	240
	5.0	2.5	180	220	240	240	240
	6.7	3.3	281	303	325	325	325
	10.0	4.9	400	428	428	456	428

¹Active ingredients, i.e. carbon black and aluminum flake²Paper substrate ignited

These formulations are capable of producing a much more controllable and uniform heater than those compositions of Examples 1 and 2 representative of prior art. Under the test conditions, it is evident that heater responses with a 200 g. water load in excess of 300° F can be obtained without the coated sheet igniting when exposed to microwave heating with no load present. It has been consistently observed that heaters produced in accordance with our invention with a mixture of carbon black, aluminum flake and clay

provide a much more uniform heater than those of Examples 1 and 2. When observed with the Hughes I.R. video system, the entire coated surface tends to heat nearly uniformly at the same rate and to nearly the same temperatures.

The data from Table III at coating weights of 3.9 (Curve A), 5.0 (Curve B), and 6.7 (Curve C) pounds per ream (3000 sq. ft.) are illustrated graphically in Fig. 1, which illustrates the heating characteristics of heaters produced according to a preferred embodiment of this invention.

EXAMPLE 4

A composition was made up containing 24 weight percent carbon black (Huber, Arosperse 47), 35 weight percent aluminum flake (Oboron, Hydrolac W60) and 41 weight percent binder composed of 1 part Lucidene 602 and 2 parts Rhoplex B-15. Paper test sheets coated with this composition were tested as in Example 1 with the results shown in Table IV.

TABLE IV

	Coat Wt. lb/rm		Heater Response in Degrees F.				
	Total	Active ²	20sec	40sec	60sec	90sec	130sec
No Load	3.5	2.1	437	456	456	470	500
	4.4	2.6	515	ign ¹	--	--	--
With Load	3.5	2.1	220	280	296	296	296
	4.4	2.6	300	375	406	398	422

¹Paper substrate ignited

²Active ingredients in coating, i.e. carbon black and aluminum flake

These compositions, while performing somewhat better than those made up of only aluminum flake and binder (Example 2) are less desirable as heating elements than the compositions of Example 3 in that it is difficult to control their performance under both load and no load conditions within acceptable temperature limits.

EXAMPLE 5

A composition was made up of 35 weight percent carbon black (Huber Arosperse 47); 35 percent clay (Georgia kaolin, Premier No. 1 Grade) and 30 percent binder (Lucidene 602). Paper test sheets coated with this composition were tested as in Example 1 with the results reported in Table V.

TABLE V

	Coat Wt. lb/rm		Heater Response in Degrees F.				
	Total	Active ¹	20sec	40sec	60sec	90sec	130sec
No Load	2.8	0.98	185	204	219	234	250
	5.0	1.75	428	ign ²	--	--	--
With Load	2.8	0.98	159	190	204	219	234
	5.0	1.75	293	347	369	369	369

¹Active ingredients in coating, i.e. carbon black

²Paper substrate ignited

Comparison of the test results obtained in this example with those of Example 1 indicates that the addition of a temperature moderator, in this case clay, has little effect on heater response temperature when carbon black is the sole microwave reactive component of the composition.

EXAMPLE 6

A composition similar to that of Example 3 was prepared with 19 weight percent carbon black, 27 weight percent aluminum flake, 18 percent kaolin, and 34 weight percent binder from a 1:2 mixture of Lucidene 602 and Rhoplex B-15.

The solids, viscosity and surface tension of the formulation was adjusted by the addition of water, alcohol and carboxymethyl cellulose as necessary for excellent runnability on a full scale gravure printing press at 250 ft/min. With reference to Fig. 2 of the drawings, test specimens were prepared by rotogravure printing and identified as follows.

Specimen	Printing Apparatus	Coating Weight lb./3000 sq ft
M	85 line screen gravure cylinder	4.5
N	100 line screen gravure cylinder	4.0
O	135 line screen gravure cylinder	2.2

A metallized film/paper laminate from a commercial popcorn package (Specimen P) was taken as a basis for comparison. The specimens were tested under no load conditions in the microwave oven as in Example 1. The results plotted in Fig. 2 clearly show that under these conditions, coat weights of 4 to 4.5 lb/3000 sq. ft. gave heating response equal to or superior to a commercial metallized film when tested in a microwave oven.

The foregoing examples illustrate the unexpected advantages of the microwave interactive coating compositions of this invention as compared with those of the prior art and other two component pigment compositions containing finely divided metal or finely divided carbon as the active ingredient.

Claims

1. A microwave interactive coating composition comprising finely divided carbon, a dielectric binder and one or both of the following components:
a finely divided inert solid temperature moderator material, and
at least one finely divided microwave reactive metallic component.
2. A microwave interactive coating composition as defined in Claim 1 wherein said metallic component is selected from the group consisting of aluminum, tin, bronze and nickel, wherein said inert solid is selected from the group consisting of alumina, alumina hydrate, silica, titanium oxides, aluminosilicates, clay, and calcium carbonate, and wherein said binder is a water based latex emulsion or an acrylic latex.
3. A microwave interactive coating composition as defined in Claim 1 or 2 wherein said carbon is graphite or carbon black.
4. A microwave interactive coating composition as defined in any of the Claims 1 to 3 wherein the ratio of binder solids to other solid components is in the range of about 0.3:1 to about 1:1.
5. A microwave interactive coating composition as defined in any of the Claims 1 to 4 wherein the metallic component is aluminum flake.
6. A microwave interactive coating composition as defined in Claim 5 wherein the relative proportions of aluminum to carbon by weight is within the range of 1:2 to 2:1.
7. A microwave interactive coating composition as defined in Claim 1 wherein the particulate inert solid content is in the range of from about 10 to about 35 percent by weight of the total weight of the solids in the composition.
8. A microwave interactive heating element comprising a microwave transparent substrate coated with a microwave interactive coating composition according to any of the preceding Claims.

9. A microwave interactive heating element as defined in Claim 8 wherein said substrate is paper or paperboard, a nonwoven or a heat stable polyester film laminated on a support structure of paper or paperboard.

10. A microwave interactive heating element as defined in Claim 8 or 9 comprising paper or paperboard
 5 coated with from about 3.26 to about 32.6 g/m² of a microwave interactive composition comprising from about 15 to about 30 weight percent carbon black, from about 15 to about 30 percent by weight aluminum flake, from about 10 to about 35 weight percent inert pigment and from about 30 to about 40 weight percent acrylic solids.

10

15

20

25

30


35

40

45

50

55



Neu eingereicht / Ni
Nouvellement déposé

Fig. 1.





Fig. 2.



(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 357 008 A3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **89115953.5**

(51) Int. Cl.⁵: **B65D 81/34, C09D 5/38**

(22) Date of filing: **30.08.89**

(30) Priority: **01.09.88 US 239544**

(43) Date of publication of application:
07.03.90 Bulletin 90/10

(84) Designated Contracting States:
AT BE CH DE ES FR GB GR IT LI LU NL SE

(68) Date of deferred publication of the search report:
27.11.91 Bulletin 91/48

(71) Applicant: **JAMES RIVER CORPORATION OF VIRGINIA**
Tredegart Street P.O. Box 2218
Richmond, VA 23217(US)

(72) Inventor: **Pollart, Kenneth A.**
524 Surrey Lane
Neenah Wisconsin 54956(US)
Inventor: **Lafferty, Terrence P.**
901 Hewitt St.
Neenah Wisconsin 54956(US)

(74) Representative: **Schupfner, Gerhard D. et al**
Müller, Schupfner & Gauger Karlstrasse 5
Postfach 14 27
W-2110 Buchholz/Nordheide(DE)

(54) **Microwave interactive coating compositions and heating elements.**

(57) A microwave interactive coating composition and microwave reactive paper and paperboard heaters comprising the coating composition are disclosed. The coating compositions which comprise finely divided carbon, a finely divided microwave reactive metallic component, a powdered inert solid and a binder are capable of producing microwave reactive heaters comparable to those produced by vapor deposition of metals on a carrier film.

EP 0 357 008 A3



European
Patent Office

EUROPEAN SEARCH REPORT

Application Number

EP 89 11 5953

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
A	EP-A-0 276 654 (WADDINGTONS CARTONS LTD) * column 2, line 42 - column 4, line 19 ** column 4, line 58 - column 5, line 58 ** column 8, line 6 - line 22 *	1-3	B 65 D 81/34 C 09 D 5/38
A	US-A-4 518 651 (W. R. WOLFE) * claims 1-8 *	1-3	
A	US-A-3 846 157 (E. HALBERSTADT) * the whole document *	1-3	
A	FR-A-2 367 002 (C. EDELMANN GMBH) * claims 1,2,4,5; figure 3 *	1,2,5	
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			B 65 D C 09 D B 32 B
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of search 04 October 91	Examiner PERNICE, C.
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document			